

ThermoFlex® **TURBO** Brights

- Turbo adhesive allows a low temperature and quick press time, which eliminates press marks
- Durable, weeds easily, and has a soft hand and strong grip
- Has a beautiful shine with a soft, metallic-like finish
- Does not encourage dye-migration since it has a low heat and quick press time
- Pressure-sensitive carrier enables easy weeding and repositioning



Gold
TFTB-14921*



Rose Gold
TFTB-14922*



Copper
TFTB-14924*



Silver
TFTB-14931*



Green
TFTB-14646*



Dark Copper
TFTB-14647*



Royal Blue
TFTB-14648*



Pink
TFTB-14925*



Red
TFTB-14926*



Blue
TFTB-14927*



Lavender
TFTB-14928*

* This product cannot be layered beneath anything.



CPSIA
COMPLIANT



SpecialtyMaterials.com | 877.437.8556

Specialty
Materials™

Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics. All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability, whatsoever, in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

Copyright © 2022, Specialty Materials & Digital Decoration, LLC. All rights reserved. Tulsa, OK 74107 | 866-437-8599

ThermoFlex® **TURBO** Brights

Acceptable Fabrics

Cotton, Uncoated Polyester, Fabric Blends, Spandex, Lycra, Wool, Linen, and **Nylon** (See Special Pressing Instructions for Nylon)

Sizing Available

Available Widths (in.): 15" and 20"

Available Lengths (ft.): 15', 30', 45', 60', 90', and 150' rolls

Thickness

4 mils/100 microns

Special Precautions

***This product cannot be layered beneath anything.**

Application Instructions for Cotton, Polyester, & Cotton/Polyester Blends



45° Blade



Cut this material in mirror image



270°F



Medium, even pressure



Press for 5 Seconds



Peel warm



Turn inside-out, wash warm, regular cycle, mild detergent. Do not use bleach. Tumble dry normal. Do not iron directly onto this material. Suitable for dry-cleaning.

Application Instructions for Nylon



45° Blade



Cut this material in mirror image



300°F



Medium, even pressure



Pre-press garment for 5 seconds, press material for 5 seconds



Peel warm, cover with silicone sheet and re-press for 10 seconds.



Turn inside-out, wash warm, regular cycle, mild detergent. Do not use bleach. Tumble dry normal. Do not iron directly onto this material. Suitable for dry-cleaning.

SpecialtyMaterials.com | 877.437.8556

Specialty
Materials™

Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics. All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability, whatsoever, in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

Copyright © 2022, Specialty Materials & Digital Decoration, LLC. All rights reserved. Tulsa, OK 74107 | 866-437-8599