





Acceptable Fabrics

Cotton, Uncoated Polyester, Fabric Blends, Spandex, Lycra, Wool, Linen, and Nylon (See separate pressing Instructions for Nylon).

Chalkboard A

Available Widths (in.): *12", 15" and 20" **Available Lengths (ft.):** 15', 30', 45', 60', 90', and 150' rolls *12" x 150' only

Thickness
3.7 mils/95 microns

Turbo adhesive allows a low temperature and quick press time, which eliminates press marks. Durable, weeds easily, and has a soft hand and strong grip. Chalk can be wiped away easily with a wet cloth. Pressure-sensitive carrier enables easy weeding and repositioning.



Chalkboard CB-4950



CUTTING

45° Blade Recommended



PRESSING

Medium, even pressure



TIMING

5 Seconds Nylon: Pre-press garment for 5 seconds, press material for 5 seconds.



WASHING

Turn inside-out, wash warm, regular cycle, mild detergent. Do not use bleach. Tumble dry normal. Do not iron directly onto this material. Suitable for dry-cleaning.



MIRRORING

Cut this material in mirror image.



TEMPERATURE

270°F Nylon: 300°F



PEELING

Peel warm Nylon: Peel warm, cover with silicone sheet and re-press for 10 seconds.



LASER COMPATIBLE

This product contains no PVC and will not emit hazardous fumes.