Super Silver
SS-5200

Super Gold
SG-5250

Brilliant Rainbow
BR-5202*

Brilliant Aqua
BA-5203*


Brilliant Red BR-5204*

Brilliant Silver BS-5205★

Brilliant Fuchsia BF-5206★



Brilliant Royal Blue BB-5209★



Brilliant Amethyst BA-5211 *

> Brilliant Pink BP-5212*

Brilliant Green

Brilliant Clear BC-5220 ★

Brilliant Gold BG-5255*

Brilliant Light
Gold BG-5260 *

Brilliant Rose Gold BG-5265

DecoFILM®

- Add value to your fashion designs with the brilliant accent of reflective metals
- The Super styles offer a slightly softer hand and stretchability
- The Brilliant styles offer a smoother, chrome-like surface that are dimensionally stable
- Super Silver and Super Gold are Oeko-Tex Class II Certified
- Pressure sensitive carrier enables easier weeding

Acceptable Fabrics

Cotton, Uncoated Polyester, Fabric Blends, Spandex*, Lycra*, Wool, Linen *Spandex and Lycra can be used ONLY using Super Colors Excluding Nylon

Sizing Available

Available Widths (in.): 19.5" only Available Lengths (ft.):

Super Silver & Gold: 15', 30', 45', 60', and 81' rolls Brilliant Colors: 15', 30', 45', 60', 90' and 162' rolls

Special Precautions

*Brilliant colors will not stretch or layer. Brilliant colors CAN be sublimated, excluding the Silver, Gold, Light Gold & Rose Gold. Brilliant Rainbow is slightly translucent and will take on the color of the garment, especially black and dark garments.

Warning: Super Silver & Gold: In order to avoid any color fading after washing, you must press the material with silicone paper for an additional 3 seconds, if not, the washing resistance is considerably reduced, therefore any claims regarding color fading WILL NOT be acknowledged in the future.



Thickness

Supers: 2.4 mils/60 microns Brilliants: 4 mils/100 microns



45° Blade



Cut this material in mirror image



310°F - 330°F



Firm, even pressure



10-15 Seconds



Peel Cold



Super Silver & Gold - Wash inside out, gentle cycle, cold water, tumble dry low. Suitable for dry-cleaning. All others - HAND WASH ONLY!



To sublimate: Heat sublimation on top of already pressed vinyl at 390°F for 30 seconds *Paper heat settings may differ





Test on dazzle cloth and other moisture-wicking polyesters. Moisture-wicking materials have better adhesion when washed and dried using no fabric softener or blotted with rubbing alcohol before pressing. Be advised that dye migration has occurred with low energy dyes in polyester and poly-blend fabrics. All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability, whatsoever, in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.